

Product Name

Highshield Roof Enamel

Product Description

Highshield Roof Enamel is premium durable alkyd enamel for roof application.



Product benefit

Anti fading / anti yellowing: Highshield is developed with special grades of alkyd resin and inorganic pigment combination that retains colour as it is for years.

Anti-Rust: Highshield has very good anti-corrosive property to protect roof for long term.

Non Toxic Film: The dry film of this product is non - toxic

and safe for application on surfaces used to collect drinking water. To collect drinking water, care must be taken to disconnect down pipes before painting and allow a heavy shower to wash the surface before reconnecting.

DPUR: Highshield roof enamel film is very tough and glossy that does not allow dirt to accumulate that gives new look for years.

Product features

Washability	Excellent
Available Packs	1 Lit, 4 Lit, 10 Lit, 20 Lit
Finish	Very Smooth - Gloss
Coverage	Coverage - 14-16 Sqm/lit/coat* *Actual coverage may vary from the quoted coverage due to factors such as method and condition of application and surface roughness and porosity.
Colour Options	Roof shade card

Areas of Application

The areas of application are metal roof, timber cladding, metal and wooden exterior surfaces.

How to Apply


Pre Painting Steps



Remove all dust, dirt and grease from the surface.



Fill nail-holes cracks etc with suitable filler and sand smooth using 220-mesh sandpaper.



If some mould or fungus is present on the surface, wash it with a commercially available bleaching agent and then treat with anti-fungal solution.




Apply suitable sealer or primer to prepare an even surface.

Paint Application / System

- Stir the contents of this container thoroughly before and during use. Apply uniformly two coats after proper surface preparation and priming.
- For weathered galvanized iron and zincalume apply Metacare AP 10 Etch primer or Metalprep Interior/Exterior Galvo Enamel Primer finish with two coats of Highshield Roof Enamel Gloss.
- For bare steel apply Metacare AP 10 Etch primer or Metalprep Interior/Exterior Galvo Enamel Primer. Finish with two coats of Highshield Roof Enamel Gloss.

Drying Time



Touch Dry	4hrs
Recoating Time	16hrs

Finish - Type / Category

Interior / Exterior Premium Enamel.

Additional Information

Gloss level @ 60°	Gloss - 85-100 Unit
Method of application	Brush, roller or spray. Please use the method best suited to your requirement and skill. Use of a synthetic or mohair sleeve of 5 mm nap is suggested on flat surfaces. For airless spray application, optimum pressure of 2200 psi and nozzle size of 0.011-0.013 inches is suggested as a guideline.
Flammability	Highly flammable, UN 1263, PG III
Safety Precautions	<ul style="list-style-type: none"> • Do not apply when surface temperature is below 10°C. • Provide adequate ventilation during use. • Keep out of reach of children. • Check cross cut adhesion of old paint before repainting. • Under normal conditions a week's curing is required to develop full hardness & resistant properties.

DISCLAIMER:

Although the facts and suggestions in this publication are based on our own research and are believed reliable, we cannot assume any responsibility for performance or results obtained through the use of our products herein described, nor do we accept any liability for loss or damages directly caused by our products. The user is held to check the quality, safety and all other properties of our product prior to use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license.

 <p>APCO BRILLIANT PAINTS, BRILLIANT COLOURS (Division of Asian Paints (SP) Limited)</p>	<p>FACTORY: P.O. Box 694, Lautoka, FIJI. Ph: 679 6662799; Fax: 679 - 6663959 Email: contact.fiji@apcocoatings.com</p>	<p>SUVA OFFICE: P.O. Box 4202, Samabula, Suva, FIJI. Ph : (679) 3371267/68; Fax: (679) 3371269 Email: contact.fiji@apcocoatings.com</p>
--	--	--