

Rapidpave Paving Enamel

Rapidpave paving enamel is a premium quality single pack polyurethane based paint with good wear resistance properties.

PRODUCT BENEFITS

Good wear and tear resistance

Antislippery

Quick dry



PRODUCT FEATURES

AVAILABLE PACKS



COVERAGE



Coverage 12-14 sqm/ltr**

Actual coverage may vary from the quoted coverage due to factors such as method & condition of application and surface roughness and porosity.

AREAS OF APPLICATION



Protection of driveways, path and workshop floors made with timber & concrete.

HOW TO APPLY

SURFACE PREPARATION

Previously Unpainted Timber Floors -Sand the surface smooth and wipe it clean. Previously Unpainted Concrete Floors - Smooth bare concrete must be acid etched with diluted hydrochloric acid. Flush the surface with sufficient fresh water. Allow complete drying for 3-4 days. Previously painted surface shall be subjected to thorough removal of loose & flaking paint. Oil, grease & other contaminants shall be removed by cleaning with mild detergent solutions.

APPLICATION PROCESS

Stir the contents thoroughly before and during use. Apply uniformly direct from container. When applying over an unknown coating, please test the adhesion & compatibility of this product over a small test area. On previously unpainted timber floors apply two coats of rapid paving enamel. 10% Thinning recommended for first coat. On new concrete surfaces no primer is required. For superior performance apply APCO AP 10 etch primer. Apply first coat of Rapidpave Paving Enamel with 10% thinning followed by second coat with minimum thinning. For unsound painted concrete surfaces, remove all paint until bare substrate. For superior performance apply APCO AP 10 Etch primer. Apply first coat of Rapidpave Paving Enamel with 10% thinning followed by second coat with minimum thinning.

ADDITIONAL INFORMATION

DRYING TIME

TOUCH DRY



20
MINUTES

Gloss level @ 60°:

Gloss - 20- 35 unit

Method of application: Brush, Roller and Spray

Highly flammable, Dangerous goods class 3.2, Flash point 32°C, UN 1263, PG III.HAZCHEM 3[Y]E

RECOAT



2 hours

SAFETY PRECAUTION

- > Do not apply when surface temperature is below 10°C.
- > Provide adequate ventilation during use.
- > Keep out of reach of children.
- > Check cross cut adhesion of old paint before repainting.
- > Under normal conditions a week's curing is required to develop full hardness & resistance properties.

SAFETY INFORMATION

- > If swallowed give water to dilute. Do not induce vomiting. Get medical attention.
- > EYES: Hold open and flush with running water for at least 15 minutes.
- > Skin: Remove contaminated clothes and wash skin thoroughly with soap and water.
- > Inhalation: Remove to fresh air. If any symptoms persist, seek prompt medical attention.
- > Thinner / Cleanup - Thinner 600/Mineral turps. Though product is designed to be applied undiluted by brush, up to 5% thinner can be used for ease of application. For spraying, up to 10% thinner required depending on climatic condition.