

Product Name

Timbercare Tuffkote 342 Clear

Product Description

Timbercare Tuffkote 342 Clear is high quality Interior two pack polyurethane clear finish for various wood substrates.

Product benefit

- Excellent Marr resistance and Toughness
- Enhance Beauty of wood
- Excellent Abrasion resistance
- Quick Dry

Product features

Washability	Excellent
Available Packs	1 Lit, 4 Lit
Sheen Variants	Gloss, Semi Gloss and Matt
Coverage	Coverage - 12-14 Sqm/lit/coat* *Actual coverage may vary from the quoted coverage due to factors such as method and condition of application and surface roughness and porosity.
Colour Options	Clear

Areas of Application

Dressed timber furniture, table tops, hand rails, doors and window frames and floors.

How to Apply

Pre Painting Steps



Remove all wax, grease by cleaning with Apco Thinner 904.



Fill the surface imperfections like nail-holes, cracks etc by suitable wood filler. Sand smooth the surface dust off.




Sand the surface uniformly along the grain marks and dust off the area to be painted.

Paint Application / System

- Stir the base portion thoroughly, add hardener part and mix well
- On new timber, one coat of Tufkote matt may be used as a sealer coat. Sand the surface
- Smooth and follow with two coats of Tufkote in desired finishes
- On previously painted surfaces, carry out thorough sanding and dust off the area. Follow with two coats of Tufkote in desired finishes.

Drying Time



Touch Dry	2 hrs
Recoating Time	16 hrs

Finish - Type / Category

Two Pack Polyurethane

Additional Information

Gloss level @ 60°	Gloss -85-100 Unit Semi Gloss- 20-50 unit Matt: Below 20 unit
Mixing Ratio	1:1 by Volume Pot Life @ 25 °C - 6 Hrs
Flammability	Highly flammable, Dangerous goods clause 3.2. Flash Point 230 C Part A UN 1263 Part B UN No 2206 PG III Keep away from sources of ignition.
Safety Precautions	<ul style="list-style-type: none">• Do not apply when surface temperature is below 10°C.• Provide adequate ventilation during use.• Keep out of reach of children.• Check cross cut adhesion of old paint before repainting.• Under normal conditions a week's curing is required to develop full hardness & resistant properties.

DISCLAIMER:

Although the facts and suggestions in this publication are based on our own research and are believed reliable, we cannot assume any responsibility for performance or results obtained through the use of our products herein described, nor do we accept any liability for loss or damages directly caused by our products. The user is held to check the quality, safety and all other properties of our product prior to use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license.

 <p>APCO BRILLIANT PAINTS, BRILLIANT COLOURS (Division of Asian Paints (SP) Limited)</p>	<p>FACTORY: P.O. Box 694, Lautoka, FIJI. Ph: 679 6662799; Fax: 679 - 6663959 Email: contact.fiji@apccoatings.com</p>	<p>SUVA OFFICE: P.O. Box 4202, Samabula, Suva, FIJI. Ph : (679) 3371267/68; Fax: (679) 3371269 Email: contact.fiji@apccoatings.com</p>
--	---	---