

Timbercare Alkyd Clear

Alkyd clear is premium quality alkyd based clear finish having excellent flow and leveling properties. It is single pack easy to use clear finish which enhances beauty of wood.

PRODUCT BENEFITS

High Gloss

Excellent flow and leveling

Non yellowing film





PRODUCT FEATURES

AVAILABLE PACKS



COVERAGE



Coverage 12-14 sqm/ltr**

Actual coverage may vary from the quoted coverage due to factors such as method & condition of application and surface roughness and porosity.

AREAS OF APPLICATION









Dressed timber furniture, doors, veneers, wall panelling etc

HOW TO APPLY

SURFACE PREPARATION

Ensure that timber to be painted is clean and dry. Remove all wax, grease and oil by cleaning with thinner. Carry out sanding along the grain marks using fine sand paper. Dust off entire area to be painted. Fill surface imperfections like nail holes and cracks etc by suitable filler. Sand smooth surface using fine sand paper and dust off.

APPLICATION PROCESS

For better finish on new timber surfaces, apply one or two coats of Timbercare Brushable sanding sealer before application of this product.

On previously varnished surfaces , apply one or two coats of Alkyd clear with minimum 16 hrs recoating interval. Light sanding between the coats with 320 mesh sandpaper is recommended.

Caution: Allow enough time for proper curing of paint film. Always carry out sanding of wooden surfaces along the grain marks. Use only the recommended thinner for dilution and cleaning.

ADDITIONAL INFORMATION

DRYING TIME

TOUCH DRY



2 HOURS

RECOAT



16 hours Recoat

Gloss @ 60°:

Gloss - min 85 unit

Method of application: Brush and Spray.

Highly flammable, Dangerous goods class 3.2, Flash point 32°C, UN 1263, PG III. HAZCHEM 3[Y]E

Clear Finishes for Interior Timber Substrates



SAFETY PRECAUTION

- > Do not apply when surface temperature is below 10°C.
- > Provide adequate ventilation during use.
- > Keep out of reach of children.
- > Check cross cut adhesion of old paint before repainting.
- > Under normal conditions a week's curing is required to develop full hardness & resistance properties.

SAFETY INFORMATION

- > If swallowed give water to dilute. Do not induce vomiting. Get medical attention.
- > EYES: Hold open and flush with running water for at least 15 minutes.
- > Skin: Remove contaminated clothes and wash skin thoroughly with soap and water.
- > Inhalation: Remove to fresh air. If any symptoms persist, seek prompt medical attention.
- > Thinner / Cleanup Thinner 600/Mineral turps. Though product is designed to be applied undiluted by brush, up to 10% thinner can be used for ease of application. For spraying, up to 30% thinner required depending on climatic condition.