

Timbercare Tufkote 342 clear base

Tufkote 342 clear interior is premium quality two pack polyurethane finish which exhibits excellent marr resistance and toughness.



PRODUCT BENEFITS

- Excellent marr resistance
- Excellent Toughness
- Excellent abrasion resistance



PRODUCT FEATURES

AVAILABLE PACKS



COVERAGE



Coverage 12-14 sqm/ltr**

Actual coverage may vary from the quoted coverage due to factors such as method & condition of application and surface roughness and porosity.

AREAS OF APPLICATION



Dressed timber furniture, table tops, hand rails, doors and window frames and floors.

HOW TO APPLY

SURFACE PREPARATION

Ensure that timber to be painted is clean and dry. Remove all wax, grease and oil by cleaning with thinner. Carry out sanding along the grain marks using fine sand paper. Dust off entire area to be painted. Fill surface imperfections like nail holes and cracks etc by suitable filler. Sand smooth surface using fine sand paper and dust off.

APPLICATION PROCESS

On new timber one coat of Tufkote 342 matt may be used as sealer coat if necessary. Sand the surface smooth and follow with two coats of Tufkote 342 in desired finishes.

On previously painted surfaces, carry out thorough sanding and dust off the area. Follow with two coats of Tufkote 342 in desired finishes. Ensure thorough mixing of semi-gloss and matt version before application.

Caution: Keep both base and hardener on a clean and dry area. Refer material safety data sheet before using the product. Do not filter semi-gloss and matt finishes prior to use

ADDITIONAL INFORMATION

DRYING TIME

TOUCH DRY



2 HOURS

Gloss @ 60°:

Gloss - min 85 units


Semi-gloss -20-50 units

Matt - 0 - 5 units

Method of application: Brush and Spray.

Highly flammable, Dangerous goods class 3.2, Flash point 32°C, UN 1263, PG III. HAZCHEM 3[Y]E

RECOAT



16 hours
Recoat

SAFETY PRECAUTION

- > Do not apply when surface temperature is below 10°C.
- > Provide adequate ventilation during use.
- > Keep out of reach of children.
- > Check cross cut adhesion of old paint before repainting.
- > Under normal conditions a week's curing is required to develop full hardness & resistance properties.

SAFETY INFORMATION

- > If swallowed give water to dilute. Do not induce vomiting. Get medical attention.
- > EYES: Hold open and flush with running water for at least 15 minutes.
- > Skin: Remove contaminated clothes and wash skin thoroughly with soap and water.
- > Inhalation: Remove to fresh air. If any symptoms persist, seek prompt medical attention.
- > Thinner / Cleanup - Thinner 604. Though product is designed to be applied undiluted by brush, up to 5% thinner can be used for ease of application. For spraying, up to 10% thinner required depending on climatic condition.